

Product Datasheet: ARC S1PW

General Purpose, Sprayable, Corrosion Protection Coating

100% solids, reinforced thin film coating to protect structures against chemical, erosion and corrosion attack. ARC S1PW is certified for cold water service requiring NSF 600 compliance and NSF 61 certification. ARC S1PW is designed to:

- Provide excellent barrier protection against erosion, corrosion and chemical attack
- Meet all requirements of NSF 61 for potable, cold water service
- Easily apply by brush, roller or plural component spray

Application Areas

- Crude oil storage tanks
- Chemical storage tanks
- Wastewater clarifiers
- Structural Steel
- Thickener tanks
- Cooling water systems

pipes, pumps, valves and fittings

Potable water tanks,

Packaging and Coverage

Nominal based on a 375 µm (15 mil) DFT

1125 ml cartridge covers 3.00 m² (32.30 ft²)

 5 liter kit covers 13.33 m² (143.52 ft²) 16 liter kit covers 42.67 m² (459.26 ft²)

Note: Components are pre-measured and pre-weighed. Each kit includes mixing and application

5 liter kit includes tools.

instructions.

Colors: White or blue







Features and Benefits

- Ceramic reinforced
 - Resists erosion
- High dielectric resistivity
 - Allows spark testing per NACE SP0188
- Low viscosity
 - Easy to apply
- Low surface energy
 - Improves efficient flow
- Excellent adhesion
 - No underfilm corrosion
- Compliant to NSF 61 standard for cold water service
 - Complies with NSF/ANSI/ **CAN 600**
 - Non-contaminating formulation

05/23

Composition	Matrix	A modified epoxy resin reacted with polyamidoamine curing agent		
	Reinforcement (Proprietary)	Blend of fine aluminum oxide powders & micro glass flakes treated with polymeri coupling agent		
Cured Density			1.59 g/cc	92 lb/ cu.ft.
Compressive Strength		(ASTM D 695)	715 kg/cm² (70.1 MPa)	10,180 psi
Flexural Strength		(ASTM D 790)	669 kg/cm² (65.6 MPa)	9,520 psi
Flexural Modulus		(ASTM D 790)	3.9 x 10 ⁴ kg/cm ² (3.7 x 10 ³ MPa)	5.4 x 10⁵ psi
Pull-Off Adhesion	n Metal	(ASTM D 4541)	477 kg/cm ² (46.8 MPa)	6,790 psi
Tensile Elongatio	n	(ASTM D 648)	3.15%	
Shore D Durometer Hardness		(ASTM D 2240)	87	
Vertical Sag Resistance, at 21°C (70°F) and 250 μm (10 mils)			No sag	
Maximum Temperature (Dependent on service)		Wet Service (NSF-CLD 23) Dry Service (General) Wet Service (General)	62°C 52°C	144°F 126°F
Shelf life (unopened containers)		1 year [stored between 10°C (50°F) and 32°C (90°F) in dry, covered facility]		



A.W. Chesterton Company 860 Salem Street, Groveland, MA 01834 USA Tel +1 978-469-6888 Toll Free 844-469-6888 arcindustrialcoatings.com ARCInfo@Chesterton.com © 2023 A.W. Chesterton Company

Registered trademark owned by A.W. Chesterton Company in USA and other countries, unless otherwise noted.

Technical Data reflect results of laboratory tests and are intended to indicate general characteristics only. Since many actual application circumstances are beyond Chesterton's knowledge and/or control, the product user must determine the suitability of the products it intends to use for its particula purpose and assume all risks and liabilities in connection therewith. CHESTERTON DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.